

# CLASS B HP

## DESCRIPTION

STIFERITE CLASS B HP is an height performance insulation board with a rigid polyisocyanurate polyiso foam core, blowing without CFC or HCFC, covered on one side with mineral saturated fiber glass and on one side with bituminous fiber glass with PPE layer.

## MAIN APPLICATIONS

Insulation of roofs also under synthetic mantles  
Insulation of floors under load  
Insulation of walls  
External thermal insulation

## GUIDELINE FOR DRAFTING OF TECHNICAL SPECIFICATIONS\*

Thermal insulation **STIFERITE CLASS B HP** in polyiso rigid foam (PIR) of thickness...(\*), covered on one side with mineral saturated fiber glass and on one side with bituminous fiber glass with PPE layer, has:

Declared thermal conductivity:  $\lambda_D = \dots$  W/mK (EN 13165 Annex A e C)

Compressive strenght: **minimum value = ... kPa (EN 826)**

Water vapour diffusion resistance factor:  **$\mu = 33$  (EN 12086)**

Water vapour diffusion resistance:  **$Z = 4.9$  m<sup>2</sup>/hPa (EN 12086)**

Water absorptin by total immersion: **WL < 2 % (EN 12087)**

Euroclass reaction to fire: **F (EN 11925-2)**

**Product of Company certified according to UNI EN ISO 9001:2000 specifications, with CE conformity mark on the whole range.**

(\* ) Not stated parameters change according to thickness. For introducing the values corresponding to the used thickness, please use the specifications indicated on this technical sheet.

## Characteristics and performances

### Isolamento Termico

Characteristics [Standard]	Description	Symbol [Units]	Value									
			Some characteristics depend on the thickness (mm)									
			-	30	40	50	60	70	80	90	100	120
Average initial thermal conductivity [EN 12667]	Value determinad at 10 °C	$\lambda_{90/90,1}$ [W/mK]	<b>0,024</b>									
Declared thermal conductivity [UNI EN 13165 annex A e C]	Value determinad at 10 °C C	$\lambda_D$ [W/mk]	<b>0,028</b> thickness 20 - 70									
			<b>0,026</b> thickness 80 - 120									
Declared thermal trasmittance	$U_D = \lambda_D / d$	$U_D$ [W/m <sup>2</sup> K]	-	<b>0.93</b>	<b>0.70</b>	<b>0.56</b>	<b>0.47</b>	<b>0.40</b>	<b>0.33</b>	<b>0.29</b>	<b>0.26</b>	<b>0.22</b>
Declared thermal resistance	$R_D = d / \lambda_D$	$R_D$ [m <sup>2</sup> K/W]	-	<b>1.07</b>	<b>1.43</b>	<b>1.79</b>	<b>2.14</b>	<b>2.50</b>	<b>3.03</b>	<b>3.49</b>	<b>3.85</b>	<b>4.62</b>

For other characteristics see back →

Other information	To obtain further technical data call <b>green numer 800840012</b>		
Technical data sheet	Stiferite CLASS B HP	Rev. 5 15/10/2008	Author: F. Raggiotto
			Verified: L. Tolin

**Technical data sheet**

**CLASS B HP**

**Characteristics and performances**

Characteristics [Standard]	Description	Symbol [Units]	Value									
			Some characteristics depend on the thickness (mm)									
			-	30	40	50	60	70	80	90	100	120
Compressive strenght [EN 826]	Value determinad at 10% deformation	$\sigma_{10} \sigma_m$ [kPa]	-	200	200	200	200	200	200	200	200	200
Dimensional stability under specified temperature and umidity [EN 1604]	48h ( $\pm 1$ ) a 70°C ( $\pm 2$ ) e 90% UR ( $\pm 5$ )	DS(TH) [% dimensions]	-	1	1	1	1	1	1	1	1	1
		[% thickness]	-	6	5	4	3	3	3	3	3	3
	48h ( $\pm 1$ ) a -20°C ( $\pm 3$ )	[% dimensions]	-	0,5	0,5	0,5	0,5	0,5	0,5	0,5	0,5	0,5
		[% thickness]	-	30	40	50	60	70	80	90	100	120
Nominal thickness [EN 823]		$d_N$ [mm]	production from 30 to 120 mm									
Board density	Average value with facing characteristics	$\rho$ [Kg/m <sup>3</sup> ]	52									
Euroclass reaction to fire [EN 13501-1] [EN 11925 -2] [EN 13823 (SBI)]	Class	Euroclass	F									
Euroclass reaction to fire [EN 11925 -2]	foam	Euroclass	E									
Specific heat capacity	Value	$C_p$ [J/kg°C]	1480									
Water vapor diffusion resistance factor [EN 12086]	Value	$\mu$ (MU)	33 $\pm$ 2									
Water vapor diffusion resistance [EN 12086]	Value	$Z$ [m <sup>2</sup> /hPa]	4.9 $\pm$ 0.1									
Water absorption [EN 12087]	Total immersion for 28 days	WL [%]	Less then 2% <sub>w</sub>									

**Tolerances and notes**

Tolerances [UNI EN 13165]	Thickness	T2 [mm]	<50 $\pm 2$ mm		from 50 to 75 $\pm 3$ mm		>75 +5 /-2 mm	
	Dimensions		< 1000 $\pm 5$ mm	from 1000 to 2000 $\pm 7,5$ mm	from 2000 to 4000 $\pm 10$ mm	> 4000 $\pm 15$ mm		
Notes	stability to the temperature	Stiferite panels are used in a range of continuous temperatures normally included between -40 °C e +120 °C. During short time they can resist also to temperatures till + 200 °C, or corresponding to the temperature of fused bitumen, without particular problems. Long exposures to the temperatures could cause deformations to the foam or to the coats, but without causing sublimation or fusion. Resistance to the torch and some other reactions to fire are characteristics connected with the kind of used panel.						
	Aspect	Any possible little areas of non-adhesion between coats and foam are originated by the production process and don't prejudice in any way the physical-mechanical properties of the panels.						

Other information	To obtain further technical data call <b>green numer 800840012</b>		
Technical data sheet	Stiferite CLASS B HP	Rev. 5 15/10/2008	Author: F. Raggiotto
			Verified: L. Tolin